


MODEL: MC4-6











ISO9001 ISO14001 OHSAS18001






Parameter Chart:


Volt	s					
Capacity((25°C)	2	4Ah			
Discharge Current Testing (25°C)		20) I ₂₀ rate (4A	,27min)	31min	
		60	7min			
Internal Res	Internal Resistance		Full Charged Battery 25°C			
Capacity Affected By Temperature			40°C		104%	
		25°C			100%	
		0°C			83%	
		-15°C			65%	
Residual Capacity (25°C)		Capac	city After 3 Mor	nths Storage	91%	
		Capac	city After 6 Mor	nths Storage	82%	
		Capacity After 12 Months Storage			65%	
Charge (Constant	Cycle (25°C)	Initial Chai T Voltag			
Voltage)	Float (25°C)		Charge V	-6.9V		
	Weight ((Appro	x)	0.7Kg		

[★]The above are average and data obtained from the first 3 charge/discharge cycles. These are not minimum values.

Residual Capacity




Discharge Current 25°C






MODEL: MC4-6

Constant voltage charging characteristics



Float Life



Constant Current Discharge Characteristics (A, 25°C)

F.V/Time	5min	10min	15min	30min	60min	2h	3h	5h	8h	10h	20h
4.80V	13.96	8.90	7.21	4.32	2.46	1.43	1.12	0.78	0.49	0.39	0.22
5.10V	11.85	8.45	6.92	4.21	2.37	1.40	1.09	0.77	0.48	0.39	0.22
5.25V	10.85	8.19	6.76	4.11	2.31	1.37	1.07	0.76	0.47	0.38	0.21
5.40V	9.95	7.92	6.57	3.99	2.25	1.34	1.05	0.75	0.46	0.37	0.20

Constant Current Discharge Characteristics (Watt, 25°C)

F.V/Time	5min	10min	15min	30min	60min	2h	3h	5h	8h	10h	20h
4.80V	75.38	48.53	39.66	24.19	14.02	8.22	6.50	4.56	2.89	2.30	1.31
5.10V	65.18	46.91	38.75	23.79	13.51	8.05	6.32	4.50	2.83	2.30	1.31
5.25V	60.22	45.85	38.19	23.43	13.28	8.01	6.26	4.48	2.80	2.26	1.25
5.40V	55.72	44.77	37.45	22.94	12.94	7.84	6.14	4.43	2.74	2.20	1.19

Capacity Factors With Different Temperature

Battery	Туре	−20°C	-10°C	0°C	5°C	10°C	20°C	25°C	30°C	40°C	45°C
Battery	6V	50%	70%	83%	85%	90%	98%	100%	102%	104%	105%

★The above are average and data obtained from the first 3 charge/discharge cycles. These are not minimum values.